



SWD Quik-Shield® | 902 Color-Fast Spray Elastomer

SWD Quik-Shield® | 902 is a 100% solids aliphatic polyurea elastomer coating. It is formulated for spray application as a high performance coating in commercial and industrial applications.

SWD Quik-Shield® | 902 is specifically designed to hold color pigments. It is also effective in situations with underlying moisture, high heat, high humidity, and changing weather conditions.

SWD Quik-Shield® | 902 is ideal for impact, abrasion and corrosion resistance applications using all types of plural component 1:1 dispensing equipment.

SWD Quik-Shield® | 902 is ideal for a variety of applications including:

- Vehicle: Truck bed liners, dump trucks, tankers, trailers
- Industrial-Commercial: Water containment areas, floor surfacing, wall coating, machinery coating
- Marine: Boat hulls, cargo holds, docks, buoys
- Agriculture: Farm equipment, trailers, silo lining
- Custom Applications: Playground equipment, secondary containment



SWD Quik-Shield® | 902 Elastomer Advantages

When compared to alternative coatings (such as paint, epoxy, rubber etc...) elastomers have several distinct advantages including;

Performance Advantages

- Abrasion and wear resistance
- High elasticity
- Water resistance
- Corrosion resistance
- Noise reduction
- Vibration dampening
- Excellent weathering ability
- High tensile strength
- Monolithic seal over porous substrates

Financial Advantages

- Quick cure times allow faster return to service
- Durability factors lower lifetime costs
- Increased service life
- Easy application



SWD Quik-Shield® | 902

Color-Fast Spray Elastomer- Specifications

CHARACTERISTICS:

DURABLE

- 100% solids aliphatic polyurea elastomer coating
- May be spray applied as thick as needed
- High tensile strength
- Chemical, corrosion and abrasion resistant

FAST CURE:

- Tack free in 7-20 seconds
- Traffic ready in 30-45 seconds
- Can be sprayed directly to a sloping or vertical surface

ENVIRONMENTALLY FRIENDLY:

- Low VOC, no solvents, no ozone-depleting properties

HIGH THERMAL STABILITY:

- Withstands temperatures from minus 15°F to 350°F (in cured state)

EXCELLENT ADHESION:

- Immediate adhesion to metal, concrete, wood, fiberglass and other substrates

EASE OF APPLICATION:

- Designed for application with high heat / high pressure spray equipment

CUSTOMIZATION:

- Accepts color pigments

SOUND ABSORPTION:

- Reduces noise levels

STORAGE:

- Store drums out of direct sunlight at temperatures not exceeding 85°F in a well-ventilated location. When stored in original unopened containers at 60°-80°F, the shelf life of SWD "Quik-Shield" 951 "A" and "B" components is six months from date of manufacture.

PROPERTIES:

LIQUID COMPONENT PROPERTIES:

	"A" Component	"B" Component
Viscosity, cps	3600	3000
Specific Gravity	1.03	1.02
Mixing ratio (by volume)	50	50

(Based on regular grade formulation at 75°F)

REACTIVITY PROFILE:

Cream Time, seconds	1-2
Tack Free Time, seconds	7-20
Cure Time @ 75°F, hours	1

FINISHED COMPONENT PROPERTIES:

Property	Procedure	Values
Core Density, pcf nominal	D-1622	52-55
Tensile Strength psi @ 75°F	D-412	2300-2500
Elongation % @ 75°F	D-412	325-375
Hardness	Shore A	93-96
Hardness	Shore D	42-49
Light Stability	QUV (3000hrs)	no change

*NOTES: ASTM Test Method Reference Number

Abrasion Resistance (ASTM H-18)

1000 Rev. (mg. wt. loss)	140
--------------------------	-----

Water Vapor Transmission (ASTM E-96)

Perms @ 40 dry mils	1.04
Perms @ 60 dry mils	.81
Perms @ 90 dry mils	.54

Coverage

Mils per 100 sf/gal	16
---------------------	----

APPLICATION:

It is essential to use a regulated high-pressure (1:1) proportioner and spray gun system capable of maintaining pressures in the 2000-2500 psi. The substrate must be clean and dust free prior to application of coating. Thoroughly mix "B" side drum (45 minutes) prior to use.

Recommended Spray Pressure: 2000 – 2800 psi

Recommended Heat Settings: Drum Heaters 75 - 80°F, Line / Pre-Heaters 150 - 155°F, Hose Heat 150 - 170°F

Note* SWD-902-CL "A" side requires use of a band heater set at 100°F for 3 – 5 hours prior to spray application for best results.

This information herein is believed to be reliable, however, unknown risks may be present. SWD Urethane Company makes no warranty, expressed or implied, concerning this product's merchantability or fitness for any particular use. The only warranty SWD Urethane Company give is that the product meets the specifications herein listed, and in the event that it does not, that SWD Urethane Company will replace, at its costs SWD Urethane Company's product. The foregoing constitutes SWD Urethane Company's sole obligation with respect to damages, whether direct, incidental or consequential, resulting from the use or performance of the product.