

QUIK-SHIELD 2020 Cementitious Roof Coating

QUIK-SHIELD[®] **2020** is a roof coating comprised of cement and proprietary resin. It offers a significant amount of value as it prevents degradation, extends the service life of any roof system, reduces energy cost, etc. QUIK-SHIELD 2020 has increased fire protection and meets class A over combustible deck.

CEMENTITIOUS BATCH

- 30-45 Gallons (114-170 L) water (variability based on site conditions)
- 10 Bags QUIK-SHIELD® cementitious mix (40 Pounds ea.(18 kg))
- 5 Gallons (19 L) QUIK-SHIELD[®] proprietary resin

Batch applied on top of 640-800 pounds (290-363 kg) white crushed limestone

APPROVALS / COMPLIANCE

ICC ESR-2532		UL: File R-9303 Construction # 136, 181, 206	
Class A Roof System		LEED	
UL Roofing Systems R-930	03 Assembly #35	CRRC: #0658-0002	
PRODUCT INFORMAT	ION		
Approximate Coverage	1 batch QUIK-SHIELD [®] Cementitious mix will cover over 1000 sq.ft.		
Product Color	White		
CRRC & Energy Star Compliant	Solar Reflectance Index (SRI) - 101%, Solar Reflectance - 81%, Thermal Emittance - 87%		
RECOMMENDED ST	ORAGE AND SHELF LIFE		
Storage temperature	as 34-120°E (1-49°C) See back for precon	ditioning of material	

Storage temperatures 34-120°F (1-49°C). See back for preconditioning of material.

• Six months shelf life from date of manufacture (unopened containers):

• Keep container tightly sealed.

• Store out of direct sunlight, in a cool dry place, avoid freezing.



PREPARATION OF SUBSTRATES

Providing the proper substrate is the responsibility of the owner, the owner's appointed representative, the contractor, and/or inspector. Preparation techniques may be required given unique/specialized application circumstances. Contact SWD for technical questions.

Remove moisture, oil, grease, dust, and debris from all surfaces prior to applying SWD products.

APPLICATION

- 1. Substrate temperature: 50-130°F (10-54°C).
- 2. Substrate surfaces must be free of moisture, oil, grease, dust, and debris.
- 3. Apply QUIK-SHIELD* spray foam, QUIK-SHIELD* 1929F coating and #6 granules, as per specifications. QUIK-SHIELD* 2020 top coat applied at a rate of 1 bag per 100 sf.
- 4. Proper application settings is the responsibility of the end user. If additional information is required, contact SWD Technical Support at 888-380-2022.

CLEANING AND MAINTENANCE

- 1. Spray equipment must be maintained in proper operating condition. Failure to adequately maintain spray equipment may result in poor product performance. Refer to your equipment manufacturer's maintenance procedures for more details.
- 2. Contact SWD for long-term equipment storage recommendations.

HEALTH & SAFETY

SWD Urethane is committed to the health and safety of our customers. SWD and QUIK-SHIELD® products should only be installed by a SWD Urethane certified contractor. Applicators are required to follow all proper handling, safety and installation procedures. For more information consult the product SDS.

WARRANTY

SWD Urethane offers 5, 10, 15, and 20 year roof warranties. All roof warranties must be registered with SWD Urethane . See SWD Limited Warranty – Roofing Systems and Coatings for required coating thickness and additional details.



The information herein is believed to be reliable; however, unknown risks may be present. SWD Urethane makes no warranty, expressed or implied, concerning this product's merchantability or fitness for any particular use. The product will meet the written liquid component specifications as indicated on the technical data sheet published at the time of the purchase. The entirety of SWD Urethane's responsibility is limited only to the cost of the SWD material. The foregoing constitutes SWD Urethane's sole obligation with respect to damages, whether direct, incidental or consequential, resulting from the use or performance of the product.

Safety is the responsibility of the owner, the owner's appointed representative, the contractor, and/or inspector. Become familiar with local, state, and federal regulations regarding chemical health, safety, and handling. For more information consult the product SDS, contact the SPFA (www.sprayfoam.org) or the ACC (www.spraypolyurethane.org). SWD Urethane | 800-828-1394 | 540 South Drew St. | Mesa, AZ 85210 | swdurethane.com